

TEST METHOD AS PER CCD-100 SECTION 5.3: CAPACITY TEST

TEST RESULTS

Using granular material, the bag was completely filled and the capacity was 26,000 cubic centimeters.

COMMENTS

- Note that the sample Passed the test as per CCD-100 Section 5.3.

TEST METHOD AS PER CCD-100 SECTION 5.4: STATIC LOAD TEST

TEST RESULTS

Material: Non Woven Polypropylene 120 GSM	
Standard Thickness – 0.008"	
Start Length	29"
End Length	29-1/8"
Difference	0.125"
% Difference	0.43%
Results	Pass

COMMENTS

- Note that the sample Passed the test as per CCD-100 Section 5.4.